



Issued 02/14

531

WEATHERSHIELD QUICK DRY EXTERIOR UNDERCOAT

Weathershield Quick Dry Exterior Undercoat from **Dulux Trade** is specifically formulated to be used with **Weathershield** topcoats to provide longer lasting protection for exterior woodwork. Its water-based formulation is quick drying and offers great flexibility to help absorb the natural movement of wood.

KEY BENEFITS

- 6 Year All Weather Protection
- Flexible Formulation
- Coverage up to 16m² per litre

PRODUCT INFORMATION

Typical Use

Ideal for use on exterior woodwork.

Pack Size

1L, 2.5L and 5L.

Colour Range

See appropriate **Dulux Trade** colour literature or visit duluxtrade.co.uk.

Composition (nominal)

Pigment: Non Lead Pigments.

Binder: Acrylic Copolymer.

Solvent: Water.

Volume Solids

36% (nominal).

SURFACE PREPARATION

To get the best results, ensure surfaces to be painted are sound, clean and dry (new surfaces particularly must be fully dry) and free from all defective or poorly adhering material such as dirt, grease or wax.

Thoroughly rub down previously painted surfaces, using 'wet flattening' methods where possible, then wipe off with a damp, lint free cloth. Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead.

Treat any knots in wood with an appropriate knotting solution. Any surface defects should be filled with the appropriate **Polycell Trade Polyfilla**.

Prime any bare metal with 1 coat of **Dulux Trade Metal Primer**. When painting areas such as plastic rainwater goods, **Weathershield** Quick Drying Exterior Gloss can be used. Apply 1 coat of **Weathershield** Quick Drying Exterior Gloss thinned to 1 part water to 10 parts paint direct to the surface.

New joinery is often factory primed using a stain basecoat (also called a dual-purpose primer). These materials quickly erode when left exposed and may need to be re-primed.



WEATHERSHIELD QUICK DRY⁵³¹ EXTERIOR UNDERCOAT

SYSTEMS INFORMATION

STIR THOROUGHLY BEFORE USE.

New or bare surfaces: Prime all bare wood with 2 coats of **Weathershield** Preservative Primer⁺ (BP)* followed by 2 coats of **Weathershield** Quick Dry Exterior Undercoat.

Previously painted surfaces: 1 coat of **Weathershield** Quick Dry Exterior Undercoat.

Finishing: Allow to dry for a minimum of 2 hours between coats, then apply the appropriate **Weathershield** topcoat.

APPLICATION METHOD

Brush only. Do not spray.

Do not use on heated surfaces, when the temperature falls below 10°C or outside when there is a likelihood of rain.

Practical Coverage

A guide to the practical coverage which can be achieved under normal conditions is up to 16m² per litre.

Spray Recommendations

This product should not be sprayed.

FURTHER SUPPORT

If you need further support, please contact the **AkzoNobel** Technical Advice Centre on [0333 222 70 70](tel:0333 222 70 70).

* **Weathershield** Preservative Primer⁺ (BP) contains 3-iodo-2-propynyl-n-butyl carbamate and propiconazole. **Use biocides safely. Always read the label and product information before use.**

Always read full Health, Safety & Environmental Information on can before use.

Drying Times

Single coat at standard thickness:

Touch Dry: 1-2 hours dependent upon temperature and humidity.

Recoat: 2-4 hours dependent upon temperature and humidity.

Cleaning Up

After use, remove as much product as possible from equipment before cleaning with water.

When this paint container is empty please ask your stockist about recycling. If you have leftover paint, please dispose of it responsibly and consider donating it to **Community RePaint**. Find out more at duluxtrade.co.uk/pp.

Transportation & Storage

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

VOC

EU limit value for this product (cat.: A/d): 130g/l (2010). This product contains max. 40g/l VOC. VOC content: Low (0.30-7.99%).



Issued 02/14

531

WEATHERSHIELD QUICK DRY EXTERIOR UNDERCOAT

Safety datasheet (SDS 531) is available free on request by telephoning the **AkzoNobel** Technical Advice Centre or by visiting duluxtrade.co.uk.

AkzoNobel, the AkzoNobel logo, the Flourish logo, Dulux Trade, Weathershield, Polycell, Polyfilla, Community RePaint and the Planet Possible logo are trademarks of the AkzoNobel group. © AkzoNobel 2014.



At Dulux Trade, we believe by working with our customers we can reduce waste and do more with the resources we have. Together we can create a better future for our planet. Join us at duluxtrade.co.uk/pp

AkzoNobel